

SALOMON'S METALEN B.V.

Reactor Grade Zirconium

Zirconium is a commercially available refractory metal with excellent corrosion resistance, good mechanical properties, very low thermal neutron cross section, and can be manufactured using standard fabrication techniques.

The various zirconium alloy grades used in water-cooled nuclear reactors are also available for nuclear waste disposal components. Reactor grade designates that the material has low hafnium content suitable for nuclear service. The hafnium is typically 0.010% maximum. The American Society for Testing and Materials (ASTM) offers widely recognized grades of zirconium alloys.

Zircaloy-2 (Grade R60802) is composed of Zr-1.5%Sn-0.15%Fe-0.1%Cr-0.05%Ni and has been predominantly used as fuel cladding in Boiling Water Reactors (BWR) and as calandria tubing in CANadian Deuterium Uranium (CANDU) reactor types.

Zircaloy-4 (Grade R60804) has removed the nickel and increased the iron content for less hydrogen uptake in certain reactor conditions. The alloy is typically used as fuel cladding in Pressurized Water Reactors (PWR) and CANDU reactors. The nominal Zircaloy-4 composition is Zr-1.5%Sn-0.2%Fe-0.1%Cr. Refinements in the ingot homogeneity have allowed tighter control of the alloy elements within the ASTM specification. Controlled Composition Zircaloy offers optimized in-reactor corrosion resistance by adjusting the alloy aim point within the ASTM specification ranges. Controlled Composition Zircaloy-4 has lower tin (1.3%) and higher iron (0.22%) than the standard grade.

Zr-2.5Nb (Grade R60904) is a binary alloy with niobium to increase the strength. The alloy has been utilized for pressure tubes in CANDU reactors. Advantages of zirconium alloys for long term nuclear waste disposal include excellent radiation stability and 100% compatibility with existing Zircaloy fuel cladding to alleviate any concerns of galvanic corrosion.

Zirconium 702 (Grade R60702), a non-reactor grade, has 4.5% maximum hafnium.

Zirconium alloys have superior thermal properties compared to other traditional materials in consideration for spent nuclear fuel containers. Zirconium alloys have a thermal conductivity more than 30% higher than stainless steel alloys. The linear coefficient of thermal expansion for Zirconium alloys is nearly one-third the value for stainless steel giving zirconium alloys superior dimensional stability at elevated temperatures. This is an advantage in nuclear waste containers where temperatures could exceed 200°C for hundreds of years.

Zircaloy-2 and Zircaloy-4 have a hexagonal close-packed (HCP) crystal structure at room temperature as an alpha phase. The beta phase is body centered cubic (BCC) and begins to form upon heating to approximately 810°C. The fraction of beta phase increases with temperature until complete transformation to beta phase occurs at approximately 980°C. Zircaloy exhibits anisotropy as a result of the HCP crystal structure. The hexagonal crystal deforms by both slip and twinning to produce a strong preferred orientation of the crystals (texture) during cold working. Typically, cold rolled Zircaloy strip will have a strong normal texture where most of the basal poles of the hexagonal crystals are orientated about 35 degrees to the transverse plane of the strip. The anisotropic properties of Zircaloy strip results in significantly higher yield strength values in the transverse direction. The control of crystallographic orientation allows designers to optimize material properties.

SALOMON'S METALEN B.V.

Zirconium Alloy Properties

Zirconium resists corrosive attack in most organic and mineral acids, strong alkalis, and some molten salts. Solutions of nitric acid (HNO_3), sulfuric acid (H_2SO_4), and hydrochloric acid (HCl) with impurities of ferric, cupric and nitrate ions generally result in corrosion rates of less than 0.13 mm/a (5 mpy) even at temperatures well above the boiling point curve. A tightly adherent and protective oxide film protects the metal-oxide interface to provide corrosion resistance. An additional benefit for zirconium alloys in long-term geological disposal options is the inert nature of zirconium oxide. Application of zirconium alloys alleviates the concern of nickel and chromium contamination in the ground water in severely corroded spent fuel containers.

Zirconium alloys are available in a wide variety of sizes and shapes including plate, strip, sheet, foil, tubular products, rod, and wire. Wrought products are typically supplied in an annealed and conditioned form.

SALOMON'S METALEN B.V.

THERMAL NEUTRON CROSS SECTIONS (BARNs)

Magnesium	0.059
Lead	0.17
Zirconium	0.18
Zircaloy-4	0.22
Aluminum	0.23
Iron	2.56
Austenitic Stainless Steel	3.1
Nickel	4.5
Titanium	6.1
Hafnium	104
Boron	750
Cadmium	2,520
Gadolinium	48,890

COMPOSITION (WEIGHT PERCENT)

Name	Zircaloy-2	Zircaloy-4	Zr-2.5Nb
UNS Grade	R60802	R60804	R60904
Tin	1.20-1.70	1.20-1.70	---
Iron	0.07-0.20	0.18-0.24	---
Chromium	0.05-0.15	0.07-0.13	---
Nickel	0.03-0.08	---	---
Niobium	---	---	2.40-2.80
Oxygen	Per P.O.	Per P.O.	Per P.O.
Iron + Chromium + Nickel	0.18-0.38	---	---
Iron + Chromium	---	0.28-0.37	---

MAXIMUM IMPURITIES, WEIGHT %

Name	Zircaloy-2	Zircaloy-4	Zr2.5Nb
Aluminum	0.0075	0.0075	0.0075
Boron	0.00005	0.00005	0.00005
Cadmium	0.00005	0.00005	0.00005
Carbon	0.027	0.027	0.027
Chromium	---	---	0.010
Cobalt	0.0020	0.0020	0.0020
Copper	0.0050	0.0050	0.0050
Hafnium	0.010	0.010	0.005
Hydrogen	0.0025	0.0025	0.0010
Iron	---	---	0.150
Magnesium	0.0020	0.0020	0.0020
Molybdenum	0.0050	0.0050	0.0050
Nickel	---	0.0070	0.0070
Nitrogen	0.0080	0.0080	0.0065
Phosphorus	---	---	0.0020
Silicon	0.0120	0.0120	0.010
Tin	---	---	0.0050
Tungsten	0.010	0.010	0.005
Titanium	0.0050	0.0050	0.0050
Uranium (total)	0.00035	0.00035	0.00035

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein.

SALOMON'S METALEN B.V.

PROPERTIES OF ZIRCALOY-4

Density	6.55 g/cc (0.237 lbs/cu.-in.)
Coefficient of Thermal Expansion at 25°C	6 µm/m °C (3.3 µin/in-°F)
Heat Capacity	0.285 J/g-°C (0.07 BTU/lb-°C)
Thermal Conductivity	21.5 Watts/m-K (149 BTU-in/hr-ft ² -°F)
Melting Point	1850°C (3,362°F)
Alpha→Alpha + Beta Phase Transformation	~810°C
Alpha + Beta→Beta Phase Transformation	~980°C
Hardness	89 Rb average
Modulus of Elasticity	99.3 Gpa (14,402 ksi)
Poisson's Ratio	0.37
Shear Modulus	36.2 Gpa (5,249 ksi)

MECHANICAL PROPERTIES OF ZIRCALOY-4 ANNEALED 2 MM THICK STRIP

Orientation	Longitudinal		Transverse	
Test Temperature	Room Temp	288°C	Room Temp.	288°C
Ultimate Tensile Strength				
MPa	541	271	515	241
(ksi)	(78.4)	(39.3)	(74.6)	(34.9)
Yield Strength				
MPa	80	152	468	170
(ksi)	(55.2)	(22.0)	(67.8)	(25.6)
Elongation, %	28	43	29	44

CORROSION RATE DATA FOR ZIRCALOY-4

Corrosive Media	Concentration%	Temperature °C	Corrosion Rate mm/a (MPY)
HCl	70	160	0.36 (14)
HNO ₃	70	120	0.05 (2)
H ₂ SO ₄	70	150	<0.13 (<5)
CuCl ₂	0.1	144	0.03 (1)
FeCl ₃	1	135	0.18 (7)
NaCl	25	250	nil

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein.